

AMENDMENTS TO THE CLAIMS

1. (Currently amended) A method of manufacturing a single crystal without using any seed crystal, comprising the steps of:
 - (a) preparing a raw material polycrystalline rod which is 3 mm or smaller in diameter; and
 - (b) heating and melting the raw material polycrystalline rod to form a molten zone and then cooling and solidifying the molten zone successively in the length direction, such that a fiber-shaped single crystal, which is 3 mm or smaller in diameter, grows in the direction normal to the densest surface.
2. (Original) The method of manufacturing a single crystal as claimed in claim 1, wherein the single crystal is an oxide single crystal.
3. (Original) The method of manufacturing a single crystal as claimed in claim 1 or 2, wherein step (b) is performed using the Floating Zone Method.
- 4.(Original) The manufacturing method of a single crystal as claimed in claim 1 or 2, wherein step (b) is performed using the Laser Heated Pedestal Growth method.
- 5 - 7 (Cancelled)
8. (Currently amended) A method of manufacturing a single crystal comprising without using a seed crystal:
 - (a) providing a $(Y,R)_3Fe_5O_{12}$ polycrystalline rod which is 3 mm or smaller in diameter; and
 - (b) heating and melting the raw material polycrystalline rod to form a molten zone and then cooling and solidifying the molten zone

successively in the length direction, such that a fiber-shaped single crystal, which is 3 mm or smaller in diameter, grows in the direction normal to the densest surface.

9. (Previously presented) The method of manufacturing a single crystal as claimed in claim 8, wherein heating and melting the raw material polycrystalline rod to form a molten zone and then cooling and solidifying the molten zone successively in the length direction, such that a fiber-shaped single crystal, which is 3 mm or is performed using the Floated Zone Method.

10. (Previously presented) The method of manufacturing a single crystal as claimed in claim 8, wherein heating and melting the raw material polycrystalline rod to form a molten zone and then cooling and solidifying the molten zone successively in the length direction, such that a fiber-shaped single crystal, which is 3 mm is performed by the Laser Heated Pedestal Growth Method.

11 - 15 (Cancelled).

16. (Previously presented) A method of manufacturing a single crystal according to claim 8 wherein R is at least one element selected from the group consisting of Y and the rare earth elements of atomic numbers 57 to 71.

17. (Previously presented) The method of manufacturing a single crystal as claimed in claim 8 wherein the polycrystalline rod is a YIG polycrystalline rod.